



# Paver Kare®

HARDSCAPE CLEANERS & PROTECTION

## Deep Sheen WB

Paver Kare® Deep Sheen WB is the perfect treatment for concrete, clay or stone pavers, inside or out. This durable, water-borne protective treatment weather- and stain-proofs new or newly cleaned pavers, giving them a premium, vibrant gloss and shine.

Deep Sheen WB's glossy finish guards pavers against etching and staining from acidic and alkaline contaminants, including food, drinks, cleaning chemicals and more. Fast-drying, non-blushing and non-yellowing, Deep Sheen WB is ideal for paver installations of any size – new or old.

### ADVANTAGES

- Non-yellowing. Surface stays clear
- Excellent blush resistance
- Reduces clean up effort and resists construction stains
- Acid and scratch resistant
- Prevents efflorescence, dusting and spalling
- Low odor, quick drying and re-coatable
- Complies with all known national, state and district AIM VOC regulations

### Limitations

- Not suitable for use around pools, fountains or showers
- Do not freeze
- Not recommended for below-grade application
- Will not prevent water penetration through structural cracks, defects or open joints
- Not designed for application to asphaltic or painted surfaces. Always test

### TYPICAL TECHNICAL DATA

<b>FORM</b>	opaque liquid, low odor white color
<b>SPECIFIC GRAVITY</b>	1.01
<b>pH</b>	8.00
<b>WT/GAL</b>	8.44 lbs
<b>ACTIVE CONTENT</b>	20%
<b>TOTAL SOLIDS</b>	20% ASTM D 2369
<b>VOC CONTENT</b>	<100 g/L maximum
<b>FLASH POINT</b>	>212°F (>100°C)
<b>FREEZE POINT</b>	32°F (0°C)
<b>SHELF LIFE</b>	1 year in tightly sealed, unopened container

### REGULATORY COMPLIANCE

#### VOC Compliance

Paver Kare® Deep Sheen WB is compliant with the US Environmental Protection Agency's AIM VOC regulations.

Visit [www.prosoco.com/voccompliance](http://www.prosoco.com/voccompliance) to confirm compliance with individual district or state regulations.

### SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

**24-Hour Emergency Information:**  
**INFOTRAC at 800-535-5053**

# Product Data Sheet

## Paver Kare® Deep Sheen WB

### PREPARATION

Protect people, vehicles, property, plants, windows and all non masonry surfaces from product, splash, residue, fumes and wind drift. Protect and/or divert foot and auto traffic. Pavers must be clean, dry and in good repair before application.

Surface should be clean and dry. If needed, clean with appropriate Sure Klean® or Enviro Klean® product. Call Customer Care toll-free at 800-255-4255, or visit [www.prosoco.com](http://www.prosoco.com) for product recommendations.

### Surface and Air Temperatures

Temperatures should be at least 50°F (10°C), and not above 90°F (32°C) during application. If freezing conditions exist before application, let masonry thaw before application.

Do not apply during rain, to wet surfaces or when there is a chance of rain. Protect from rain for two days following application.

### Equipment

Low-pressure (<50 psi) spray application is recommended. Do not atomize. May be applied by brush or roller.

### Storage and Handling

Keep from freezing. Store in a cool, dry place. Always seal container after dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright storage of factory-sealed container in a dry place. Maintain temperatures of 45–100°F (7–38°C). Do not double stack pallets. Dispose of unused product and container in accordance with local, state and federal regulations.

### APPLICATION

Read “Preparation” and the Safety Data Sheet before use. **ALWAYS TEST** for coverage and results before overall application. Test using the following application instructions. Let the test dry thoroughly before inspection.

### Dilution & Mixing

Do not dilute or alter. Apply as packaged.

Stir thoroughly before application. Do not shake. Shaking may entrap air.

### Typical Coverage Rates

Coverage estimates depend on surface texture and porosity. Always test to ensure desired results.

#### Concrete Pavers

- 50–75 square feet per gallon
- 5–7 square meters per gallon

#### Clay Pavers

- 75–100 square feet per gallon
- 7–9 square meters per gallon

#### Stone Pavers

- 200–400 square feet per gallon
- 19–37 square meters per gallon

### Application Instructions

#### Brush or Roller

1. Saturate the entire surface. Avoid excessive overlapping.
2. Carefully brush out runs and drips.
3. Reapply, if needed, to produce an even appearance over the entire surface. Allow 30–40 minutes between applications, or until first coat is dry. Less material will be needed for the second coat.

#### Sprayer

1. Apply two or more thin, even coats to a total thickness of 2–4 mils wet. Let first coat dry 15 minutes or until it becomes tacky.
2. Apply two or more coats again, in the same manner, to produce an even appearance. Allow 30–40 minutes dry-time between each set of applications, or until first application is dry.

### Drying Time

Protect treated surfaces from water for 4 to 6 hours following application. Protect from rain for two days after application. At 70°F (21°C) treated surfaces dry:

- *To touch*: 30–40 minutes
- *Light foot traffic*: 4 hours
- *Normal traffic*: overnight

### Cleanup

Clean tools and equipment immediately with soap and water. If Deep Sheen WB dries, use Defacer Eraser® Graffiti Wipe, mineral spirits or similar solvent to clean tools and equipment.

# Product Data Sheet

## Paver Kare® Deep Sheen WB

### WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

### CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our web site at [www.prosoco.com](http://www.prosoco.com), for the name of the PROSOCO representative in your area.

### BEST PRACTICES

Do not use around pools, fountains or other water features.

Paver surfaces should be clean, dry and absorbent before application.

Clean soiled paver surfaces with Sure Klean® Light Duty Concrete Cleaner before application.

Preferred method of application is low pressure spray equipment. Use a fan-type spray tip and adjust pressure to avoid atomization of the material.

Apply thin coats (2–4 mils) evenly.

Treatment consists of two applications of two coats each.

During each application, let the first coat dry until tacky – about 15 minutes. Between applications, let the treatment dry to touch – about 30–40 minutes.

Never go it alone. If you have problems or questions, contact your local PROSOCO distributor or field representative. Or call PROSOCO technical Customer Care, toll-free at 800-255-4255.